

RM40 材料特性

1.特性参数

Parameter			Symbol	Unit	RM40
Initial Permeability			μ i		2300±25%
Flux Density		25℃	Bs	mT	550
		100℃			390
Curie Temperature			Tc	℃	230
Power Loss	25KHz 200mT	25℃	Pv	kw/m³	120
		60℃			80
		100℃			60
	100KHz 200mT	25℃	Pv	kw/m³	600
		60℃			450
		100℃			410
Resistivity			ρ	Ω *m	6. 5
Density			d	kg/m³	4800

2.特性曲线

